

Foam-Control® Geofoam is a cellular plastic material that is strong, but has very low density (1% of traditional earth materials). It is manufactured in block form and meets ASTM D6817, “Standard Specification for Rigid, Cellular Polystyrene Geofoam.” Foam-Control Geofoam is available in a range of Types to provide control of structural integrity and cost effectiveness.

The information given is deemed to be timely, accurate, and reliable for the use of Foam-Control Geofoam. Each project using Foam-Control Geofoam should be designed by a professional engineer. The engineer or project specifications should be consulted to determine the ASTM D6817 Type required for your project loading conditions.

PRODUCT		FOAM-CONTROL GEOFOAM™						
		12	15	19	22	29	39	46
Density ¹ , min.	lb/ft ³ (kg/m ³)	0.70 (11.2)	0.90 (14.4)	1.15 (18.4)	1.35 (21.6)	1.80 (28.8)	2.40 (38.4)	2.85 (45.7)
Compressive Resistance ^{1,2} @ 1% deformation, min.	psi psf (kPa)	2.2 320 (15)	3.6 520 (25)	5.8 840 (40)	7.3 1050 (50)	10.9 1570 (75)	15.0 2160 (103)	18.6 2680 (128)
Elastic Modulus, min	psi (kPa)	220 (1500)	360 (2500)	580 (4000)	730 (5000)	1090 (7500)	1500 (10300)	1860 (12800)
Flexural Strength ¹ , min.	psi (kPa)	10.0 (69)	25.0 (172)	30.0 (207)	35.0 (240)	50.0 (345)	60.0 (414)	75.0 (517)
Water Absorption by total immersion, max.,	vol. %	4.0	4.0	3.0	3.0	2.0	2.0	2.0
Oxygen Index ¹ , min.	vol. %	24	24	24	24	24	24	24
Buoyancy Force	lb/ft ³ (kg/m ³)	61.7 (990)	61.5 (980)	61.3 (980)	61.1 (980)	60.6 (970)	60.0 (960)	59.5 (950)
ASTM D6817 Compliance, Type		EPS12	EPS15	EPS19	EPS22	EPS29	EPS39	EPS46

¹ See ASTM D6817 Standard for test methods and complete information.

² Combined live and dead load stresses should not exceed the compressive resistance at 1% deformation.

Foam-Control Geofoam is used in ground fill applications where a lightweight fill material is required to reduce stresses on underlying or adjoining soils/structures.

Ready to Use.

Foam-Control Geofoam maximizes onsite installation efficiency: material arrives ready to place, no weather delays, material can be prefabricated or cut at the jobsite, no staging required, material can be inventoried, production efficiency improved, and it is easy to handle.

Design Loads.

For most applications, long-term design loads should not exceed the linear elastic range of Foam-Control Geofoam. Combined live and dead load stresses should not exceed the compressive resistance at 1% deformation.

In some specialty compressible applications, the compressive resistance at 5% and 10% deformation may be applicable. Please consult Foam-Control Geofoam Technical Bulletins for additional information.

In general earthwork applications (such as levees, dikes, berms, etc.) uplift buoyancy force must be counteracted with overburden or restraint devices, such as geogrids, geomembranes, hold down devices, etc.

Size and Shape.

Foam-Control Geofoam is produced in block form and is easily positioned at the work site. Standards sizes:

- 4' (1.2 m) widths
- 8' (2.4 m) up to 16' (4.8 m) lengths
- 1" (25 mm) to 36" (914 mm) thickness

Other sizes and fabrication can be provided by the manufacturer.

Exposure to Water and Water Vapor.

The mechanical properties of Foam-Control Geofoam are unaffected by moisture. Exposure to water or water vapor does not cause swelling.

Temperature Exposure/Flame Retardants.

Foam-Control Geofoam is able to withstand the rigors of temperature cycling, assuring long-term performance.

Although flame retardants used in the manufacture of Foam-Control Geofoam provide an important margin of safety, Foam-Control Geofoam must be considered combustible.

The maximum recommended long-term exposure temperature for Foam-Control Geofoam is 165°F (74°C).

Adhesives, Coatings, and Chemicals.

Solvents which attack Foam-Control Geofoam include esters, ketones, ethers, aromatic, and aliphatic hydrocarbons and their emulsions, among others. If Foam-Control Geofoam is to be placed in contact with materials (or their vapors) of unknown composition, pretest for compatibility at maximum exposure temperature.

Proven to meet, or exceed, building codes.

Foam-Control Geofoam is manufactured under an industry leading quality control program monitored by UL and further recognized in UL Evaluation Report UL ER11812-01. Foam-Control meets ASTM D6817, "Standard Specification for Rigid, Cellular Polystyrene Geofoam."



Termite Resistant - Perform Guard®.

One of the most destructive forces anywhere is termites. Foam-Control can be manufactured with Perform Guard, a proven and safe additive, that effectively resists termites.

Foam-Control with Perform Guard meets ICC ES AC239, "Acceptance Criteria for Termite-Resistant Foam Plastics".

Storage and Ballast.

Foam-Control Geofoam stands up well to normal short-term weather conditions encountered during installation.

Long-term exposure to sunlight causes yellowing and a slight embrittlement of the surface due to ultraviolet light. This has little effect on mechanical properties. If stored outdoors, cover Foam-Control Geofoam with opaque polyethylene film, tarps, or similar material.

Foam-Control Geofoam should be ballasted to prevent displacement by wind or high water conditions, both in storage and during all phases of placement.

Warranty.

Foam-Control Geofoam Licensees offer a product warranty ensuring physical properties.



Foam-Control products are manufactured by AFM Corporation licensees.

Copyright © 2019 AFM Corporation. All rights reserved. Printed in USA. Foam-Control and Perform Guard are registered trademarks of AFM Corporation, Lakeville, MN. The Foam-Control Geofoam logo and The Trusted Lightweight Fill Material are trademarks of AFM Corporation, Lakeville, MN.

UL logo is a registered trademark of UL LLC.

GF05-01/19



www.geofoam.com

**THE TRUSTED
LIGHTWEIGHT
FILL MATERIAL™**